
Japanese Patent Application, First Publication
No. Sho 61-65809

Publication Date: April 4, 1986

Title of the Invention: Cosmetic Make-up Composition

Application No.: Sho 59-187139

Filing Date: September 6, 1984

Int.Cl.⁴: A 61 K 7/00

Request for substantial examination: not yet submitted

Inventors: Yutaka OKUNUKI,
Masaaki ISHIWATARI,
Toshihide IKEDA, and
Tomiyuki NAMBA

Applicant: SHISEIDO CO LTD

SPECIFICATION

1. TITLE OF THE INVENTION

Cosmetic Make-up Composition


2. CLAIM

1. A cosmetic make-up composition characterized in that it contains 1% by weight - 70% by weight of an organic silicone resin defined in the following (A); 10% by weight - 98% by weight of a volatile silicone oil defined in the following (B); and 0.5% by weight - 55% by weight of powder;

(A) an organic silicone resin consisting of $R_3SiO_{1/2}$ units (wherein R represents a hydrocarbon radical or a phenyl radical) and SiO_2 units, wherein the ratio defined by $R_3SiO_{1/2}$ units : SiO_2 units ranges from 0.5/1 - 1.5/1, and


(B) at least one of volatile silicone oils represented by Formulae (I) and (II):

Formula (I)



(wherein n represents an integer of 0 - 3).

Formula (II)



(wherein n represents an integer of 4 - 6).

3. DETAILED DESCRIPTION OF THE INVENTION

[Field of Industrial Application]

feeling to the skin, as well as has an excellent anti-make-up-running effect, can be obtained, thereby achieving the present invention.


[Means for Solving the Problems]

That is, the present invention provides a cosmetic make-up composition characterized in that it contains 1% by weight - 70% by weight of an organic silicone resin defined in the following (A); 10% by weight - 98% by weight of a volatile silicone oil defined in the following (B); and 0.5% by weight - 55% by weight of powder:

(A) an organic silicone resin consisting of $R_3SiO_{1/2}$ units (wherein R represents a hydrocarbon radical or a phenyl radical) and SiO_2 units, wherein the ratio defined by $R_3SiO_{1/2}$ units : SiO_2 units ranges from 0.5/1 - 1.5/1, and


(B) at least one of volatile silicone oils represented by Formulae (I) and (II):

Formula (I)



(wherein n represents an integer of 0 - 3).

Formula (II)



(wherein n represents an integer of 4 - 6).

The organic silicone resins represented by above-mentioned (A) employed in the present invention can be easily prepared by means of hydrolysis of the corresponding known silanes.

In addition, both the chain silicone oil and the cyclic silicone oil represented by Formula (I) employed in the present invention are volatile and can be used as a solvent of the above-mentioned organic silicone resin.

The essential components of the present invention are blended in an appropriate ratio as follows:

The organic silicone resin is included in the amount of 1% by weight - 70% by weight with respect to the total weight of the whole cosmetic make-up composition, the

Example 2 Liquid rouge composition

(1)	Dimethylsiloxane 0.65 CS (n = 0)	20.0
(2)	Dimethylsiloxane 2.0 CS (n = 3)	20.0
(3)	Organic silicone resin: (CH ₃)SiO _{1/2} / SiO ₂ = 0.5 / 1	40.0
(4)	Glyceryltriisostearate	10.0
(5)	Red # 226	10.0
(6)	Perfumes	proper amount

After Components (1) - (3) were dissolved at 70°C - 80°C, while being stirred, Components (4) and (5) which had been roller-treated were dispersed into the obtained solution, and subsequently deaerated. Component (6) was added thereto, thus affording a liquid rouge composition.

The liquid rouge composition according to Example 2 exhibited excellent water resistance, oil resistance, and perspiration resistance, as well as good make-up durability such as non-adhering to a cup, while giving a refreshing feeling to the skin.

Example 3 Mascara composition

(1)	Dimethylsiloxane 1.5 CS (n = 2)	4.5
(2)	Octamethylcyclotetrasiloxane	10.0
(3)	Organic silicone resin: (CH ₃)SiO _{1/2} / SiO ₂ = 0.8 / 1	70.0
(4)	Iron black	15.0
(5)	P.O.E. (20 mol) sorbitan monolaurate	0.5
(6)	Perfumes	proper amount

After Components (1) - (3) were dissolved at 70°C - 80°C, while being stirred, Components (4) and (5) were dispersed into the obtained solution, and subsequently deaerated. Component (6) was added thereto, thus affording a mascara composition.

The mascara composition according to Example 3 exhibited an excellent make-up durability such as no make-up running due to tears, as well as hardly adhering to the eyelids.

Example 4 Make-up base composition

(1)	Kaolin	10.0
-----	--------	------

(2)	Titanium dioxide	5.0
(3)	Red iron oxide	0.3
(4)	Yellow iron oxide	0.2
(5)	Methyphenylpolysiloxane (n = 100)	20.0
(6)	Dimethylsiloxane 2 CS (n = 3)	10.0
(7)	Solid paraffin	5.0
(8)	Microcrystalline wax	4.0
(9)	Sorbitan sesquioate	1.0
(10)	Organic silicone resin: (CH ₃)SiO _{1/2} / SiO ₂ = 1 / 1	2.0
(11)	Decamethyl cyclopentasiloxane	24.5
(12)	Perfumes	proper amount

Components (1) - (4) were mixed and then pulverized. Separately, Components (5) - (11) were mixed and dissolved at 70°C - 80°C. The obtained mixture and solution were mixed while being stirred, and subsequently deaerated. Component (12) was added thereto, thus affording a make-up base composition.

The make-up base composition according to Example 4 had cosmetic effects such that the base composition supported a good spreadability of the cosmetic make-up composition which was applied on the base composition and could control the make-up running.

Example 5 Highlighter composition

(1)	Decamethylcyclopentasiloxane	95.0
(2)	Organic silicone resin: (CH ₃)SiO _{1/2} / SiO ₂ = 1.3 / 1	4.3
(3)	Titanium-mica pearl pigment	0.5
(4)	Perfumes	proper amount

Components (3) and (4) were dispersed into a mixture containing Components (1) and (2) which had been dissolved in each other while being heated, thus affording a highlighter composition.

The highlighter composition according to Example 5 was an excellent cosmetic make-up composition exhibiting good make-up durability, excellent water and oil resistance, as well as perspiration resistance. In addition, the highlighter composition gave a refreshing feeling to the skin and exhibited good spreadability.

Applicant SHISEIDO CO LTD